

GROUND TO SIZE RANDOM ROD (GRR) BLANKS

PROPERTY	TMK-320	TMK-326	TMK-3
WC (wt.%)	89.4	93.3	96.0
Co (wt.%)	10.0	6.1	3.0
Others (wt.%)	0.6	0.6	1.0
Grain Class	Submicron	Submicron	Fine
Density (g/cm³) ISO 3369	14.40	14.90	15.20
Hardness (HRA) ISO 3738	91.9	93.0	93.3
Transverse Rupture Strength (psi, min) ISO 3327	526,000	532,000	386,000