

## UNGROUND RANDOM ROD (RR) BLANKS

PROPERTY	TMK-320	TMK-290X
<b>WC (wt.%)</b>	89.4	89.9
<b>Co (wt.%)</b>	10.0	9.0
<b>Others (wt.%)</b>	0.6	1.1
<b>Grain Class</b>	Submicron	Nano
<b>Density (g/cm<sup>3</sup>)</b> ISO 3369	14.40	14.44
<b>Hardness (HRA)</b> ISO 3738	91.9	94.0
<b>Transverse Rupture Strength (psi, min)</b> ISO 3327	526,000	575,000