

## ROD BLANKS WITH COOLANT HOLES

PROPERTY	TMK-320	TMK-3020
<b>WC (wt.%)</b>	89.4	89.15
<b>Co (wt.%)</b>	10.0	10.0
<b>Others (wt.%)</b>	0.6	0.85
<b>Grain Class</b>	Submicron	Ultrafine
<b>Density (g/cm<sup>3</sup>)</b> ISO 3369	14.40	14.37
<b>Hardness (HRA)</b> ISO 3738	91.9	92.3
<b>Transverse Rupture Strength (psi, min)</b> ISO 3327	526,000	656,000