

STB AND 1000, 2000 SERIES BLANKS

PROPERTY	TMK-6	TMK-22	TMK-320	TMK-326	TMP-821
WC (wt.%)	94.0	93.9	89.4	93.3	79.3
Co (wt.%)	6.0	6.0	10.0	6.1	8
Others (wt.%)	-	0.1	0.6	0.6	12.7
Grain Class	Medium	Medium	Submicron	Submicron	Medium
Density (g/cm³) ISO 3369	14.95	14.95	14.40	14.90	12.40
Hardness (HRA) ISO 3738	91.0	92.0	91.9	93.0	91.8
Transverse Rupture Strength (psi, min) ISO 3327	332,000	393,000	526,000	532,000	275,000